

## End cutting thread mill 2.5×D, TiAlN, M: M5



## **Order data**

Order number	139521 M5
GTIN	4062406565671
Item class	11J

## **Description**

### **Version:**

Tool for **combined production** of bore, chamfer and thread **in a single operation.** No more pre-drilling required. The innovative centre cutting edge geometry makes this tool a specialist in thread production in **hardened and hard-to-machine materials.** The **TiAlN high-performance coating** achieves a top **tool life**, especially in hardened steels **up to 67 HRC**. All tools are left-hand cutting and suitable for **right-hand and left-hand threads.** 

#### Note:

Always use with cooling lubricant emulsion. (Fat content minimum 8%). In the case of steels >45 HRC: can only be used with compressed air!

Through-coolant: yes
Thread pitch: 0.8 mm
Cutting edge Ø D<sub>c</sub>: 4 mm
Cutter length l<sub>c</sub>: 2.56 mm
Overhang L<sub>1</sub>: 13.7 mm
Shank length L<sub>s</sub>: 39.8 mm
Overall length L: 57 mm

## **Technical description**

Overall length L	57 mm
Thread size	M5
Shank length L <sub>s</sub>	39.8 mm
Shank Ø D <sub>s</sub>	6 mm
Thread pitch	0.8 mm

Thread depth	12.5	
Number of clamping slots	4	
Feed $f_z$ in steel < 65 HRC	0.01 mm	
Cutter length I <sub>c</sub>	2.56 mm	
Programming radius	1.98 mm	
Overhang L <sub>1</sub>	13.7 mm	
Cutting edge Ø D <sub>c</sub>	4 mm	
Neck Ø D <sub>1</sub>	2.97 mm	
Through-coolant	yes	
Coating	TiAIN	
Thread type	M	
Thread type	M-LH	
Flank angle	60 °	
Tool material	Solid carbide	
Thread standard	DIN 13	
Shank	DIN 6535 HA with h6	
Number of cutting edges Z	4	
Application for type of drilling	up to 2×D for blind holes	
Application for type of drilling	up to 2.5×D for through holes	
Countersink angle	90°	
Cutting direction	right-hand	
Shank tolerance	h6	
Colour ring	without	
Internal/external application	Internal	
Type of product	Combination drill / thread mill	

# **User data**

	Suitability	<b>V</b> <sub>c</sub>	ISO code
Steel < 1100 N/mm <sup>2</sup>	suitable	90 m/min	Р



Steel < 1400 N/mm <sup>2</sup>	suitable	90 m/min	Р
Steel < 55 HRC	suitable	45 m/min	Н
Steel < 60 HRC	suitable	40 m/min	Н
Steel < 65 HRC	suitable	35 m/min	Н
Steel < 67 HRC	suitable	30 m/min	Н
INOX < 900 N/mm <sup>2</sup>	suitable	60 m/min	М
$INOX > 900 \text{ N/mm}^2$	suitable	60 m/min	М
Ti > 850 N/mm <sup>2</sup>	suitable	45 m/min	S
wet maximum	suitable		
Air Services	suitable		

Services

Shank grinding Type HB	129100 HB
Shank grinding Type HE	129100 HE