## Re-Bo

Solid carbide circular saw blade DIN 1838 B coarse, uncoated, Ø×thickness: 40X2mm



## Order data

| Order number | 179820 40X2   |
|--------------|---------------|
| GTIN         | 4045197246974 |
| Item class   | 17C           |

## Description

#### Version:

Top quality German product with **precision toothing** and **hollow ground mirror finish sides**. Compared to HSS saw blades, the cutting speed can be increased by a factor of 3 to 4. **DIN 1838 B coarse-toothed** with **curved teeth to form B** with chisel edge. **For cutting larger cross sections and greater cutting depths.** These blades are suitable for more universal use due to the improved chip formation and larger gullets compared to the fine-toothed version. **Note:** 

- Stable conditions of machine and component clamping are important prerequisites. If these conditions are disregarded the circular saw blade may break.
- The values for radial run-out and axial run-out are considerably better than the values specified in DIN 1840.
- · Special sizes on request.

### **Technical description**

| Ø      | 40 mm |
|--------|-------|
| Bore Ø | 10 mm |

| Thickness       | 2 mm               |  |
|-----------------|--------------------|--|
| No. of teeth Z  | 24                 |  |
| Coating         | uncoated           |  |
| Tool material   | Solid carbide      |  |
| Standard        | DIN 1838           |  |
| Through-coolant | no                 |  |
| Type of product | Circular saw blade |  |

# User data

|                                | Suitability                               | V <sub>c</sub> | ISO code |
|--------------------------------|---|----------------|----------|
| Aluminium (short<br>chipping)  | suitable only under restricted conditions | 1200 m/min     | Ν        |
| Alu > 10% Si                   | suitable only under restricted conditions | 700 m/min      | Ν        |
| Steel < 500 N/mm <sup>2</sup>  | suitable only under restricted conditions | 200 m/min      | Р        |
| Steel < 750 N/mm <sup>2</sup>  | suitable only under restricted conditions | 140 m/min      | Р        |
| Steel < 900 N/mm <sup>2</sup>  | suitable                                  | 140 m/min      | Р        |
| Steel < 1100 N/mm <sup>2</sup> | suitable                                  | 90 m/min       | Р        |
| Steel < 1400 N/mm <sup>2</sup> | suitable                                  | 40 m/min       | Р        |
| INOX < 900 N/mm <sup>2</sup>   | suitable                                  | 110 m/min      | М        |
| INOX > 900 N/mm <sup>2</sup>   | suitable                                  | 100 m/min      | М        |
| Ti > 850 N/mm²                 | suitable                                  | 90 m/min       | S        |
| GG(G)                          | suitable only under restricted conditions | 125 m/min      | К        |
| CuZn                           | suitable only under restricted conditions | 400 m/min      | Ν        |
| Graphite, GRP, CRP             | suitable only under restricted conditions | 600 m/min      | Ν        |

| Uni         | suitable only under restricted conditions |  |
|-------------|---|--|
| wet maximum | suitable                                  |  |
| dry         | suitable                                  |  |
| Air         | suitable                                  |  |