

# GARANT Diabolo solid carbide HPC drill, plain shank DIN 6535 HA, TiAIN, Ø DC h7 (mm or inch): 14,06-X



### **Order data**

Order number	122371 14,06-X		
GTIN	4062406076627		
Item class	11E		

## **Description**

#### **Version:**

Cutting chisel edge with **high centring accuracy** due to strong core and special point geometry. **Convex major cutting edges** with **defined honed edge** ensure the drill has high stability and maximum load capacity.

**Special multi-nano layer coating** for drilling in hardened steels.

#### Note:

Flute length  $L_c = L_2 + 1.5 \times D_c$ .

Form HB and HE supplied at the same price as HA.

Form **HB:** order with **No. 122362 / 122372**.

Form **HE:** order with **No. 122361 / 122371 + 129100HE**.

When drilling in hardened steels from 56 HRC, only cool using air! Delivery time: 12 working weeks

Minimum order quantity: 3 pcs

Items made to order for a specific customer:

Cancellation only up to a maximum of 3 working days after receipt of order acknowledgement. Items cannot be returned. We reserve the right to over-deliver or under-deliver by  $\pm 10\%$  (minimum 1 piece).

## **Technical description**

Flute length L <sub>c</sub>	65 mm
Standard	DIN 6537 K
Feed f in steel < 1100 N/mm <sup>2</sup>	0.32 mm/rev.
Feed f in steel < 60 HRC	0.16 mm/rev.

Shank Ø D <sub>s</sub>	16 mm		
Number of cutting edges Z	2		
Overall length L	115 mm		
Tolerance nominal Ø	h7		
Ø range	14.06 - 16.05 mm		
Series	Diabolo		
Coating	TiAlN		
Tool material	Solid carbide		
Version	4×D		
Туре	Н		
Point angle	140 degrees		
Shank	DIN 6535 HA to h6		
Through-coolant	yes, with 25 bar		
Machining strategy	HPC		
Semi-Standard	yes		
Colour ring	red		
Type of product	Jobber drill		

## **User data**

	Suitability	$\mathbf{V}_{c}$	ISO code
Steel < 500 N/mm <sup>2</sup>	suitable only under restricted conditions	120 m/min	Р
Steel < 750 N/mm <sup>2</sup>	suitable	100 m/min	Р
Steel < 900 N/mm <sup>2</sup>	suitable	85 m/min	Р
Steel < 1100 N/mm <sup>2</sup>	suitable	70 m/min	Р
Steel < 1400 N/mm <sup>2</sup>	suitable	55 m/min	Р
Steel < 55 HRC	suitable	28 m/min	Н
Steel < 60 HRC	suitable	16 m/min	Н
Steel < 65 HRC	suitable	14 m/min	Н

Steel < 67 HRC	suitable	10 m/min	Н
GG(G)	suitable	70 m/min	K
Uni	suitable		
wet maximum	suitable		
wet minimum	suitable		
Air	suitable		